Noxudol 900 Black

Underbody coating

General

Noxudol 900 is a thixotropic, chemically stabilized product consisting of bitumen, waxes, rust inhibitors and solvents. The product is used on the underside of the vehicle and offers preventive rust protection and reliable abrasion protection.

Range of application

Noxudol 900 is especially composed for car underbody and can be applied by conventional high-pressure pumps in different thicknesses. The product gives a good anticorrosive protection, de-icing salt protection and some abrasion protection depending on thickness applied. Noxudol 900 is also suitable for long time outdoor storing of industrial products, for example untreated steel surfaces, machines etc.

Instructions for use

Make sure that the surface is dry and free from oil, dirt and rust. Equipment for airless high pressure spraying 1:26> is recommended for treatment of car under bodies and fenders. The product can also be brushed on. Areas with rust should be treated with **Noxudol 750 / Mercasol 831 ML** before in order to achieve best result possible. Apply several layers of Noxudol 900 where increased protection is required. The car is ready for usage immediately after application.

Package

30000095 / 500 ml spray (12 pcs/pack.)
30000511 / 1-lit can (12 pcs/pack.)
30001405 / 5-lit can
30000408 / 20-lit can
30000701 / 60-lit drum
30000721 / 208-lit drum

Technical data

Color:	Black
Consistency.	Thixotropic
Type of film:	Elastic, dry film
Density:	1000 ± 20 kg/m³
Dry content:	68 ± 3 %
Solvent:	White spirit
Film thickness:	150 – 350 µm
Application temperature:	15 - 25° C
Removal with:	White spirit or degreasing compound
Storing time:	12 months
Storing temperature:	< 35° C
Drying time:	Approx. 12-24 h (Surface dry at +20°C)

For further information we recommend the safety data sheet or instruction on package

Issue: 2017-11-27

Auson AB. Kungsbacka, Sweden
T: +46 (0)300-56 20 00
www.auson.se

Dessa anvisningar och information är avsedda att vägleda förbrukaren vid användning av produkten och lämnas utan förbindelse. Vid oklarhet tillråds egna prov eller skriftliga råd från oss.